

PRODUCT NAME

# Fibre-Prime®

## Rustproofing Primer and Coating

MANUFACTURER

Gemite® Products Inc.

Toll Free: 888-4-GEMITE (888-443-6483)  
E-mail: [techinfo@gemite.com](mailto:techinfo@gemite.com)  
Web Site: [www.gemite.com](http://www.gemite.com)

<b>USA</b>	<b>CANADA</b>
160-3480 East Robinson Rd.	1787 Drew Road
Amherst, New York 14228	Mississauga, Ontario L5S 1J5
Phone 888-443-6483	Phone 905-672-2020
Fax 888•443•6329	Fax 905•672•6780

FEATURES

- Rustproofs reinforcing steel
- Used in rustproofing of structural steel
- Contains migrating corrosion inhibitors
- Active on anodic and cathodic sites
- Reduces rebound of shotcrete
- Allows an easy overhead patching
- An excellent bonding agent for concrete or mortars
- Self-curing
- Economical
- Hard and durable
- Superior adhesion
- Crack resistant
- Excellent freeze/thaw durability
- Waterborne = VOC Compliant
- Nontoxic
- Easy to Apply

PRODUCT DESCRIPTION

Basic Use

Rustproofing primer (slurry) for reinforcing steel in concrete. *Fibre-Prime* provides an excellent profiled surface, unlike smooth and non-absorbent epoxy, allowing easy overhead or vertical application of repair mortar or shotcrete. *Fibre-Prime* is also used as a rustproofing coating for structural steel. It also provides an excellent bondg agent to difficult to clean or oil con-



minated surfaces. Please contact Gemite Technical Service for detail instructions when bonding to contaminated surfaces.

Composition and Materials

*Fibre-Prime* is a two component material, consisting of a dry Component A and a liquid Component B. *Fibre-Prime* contains highly effective migrating corrosion inhibitors active on both, anodic as well as cathodic corrosion sites.

Limitations

Do not apply *Fibre-Prime* when the temperature is expected to be below 40°F (4°C) within 24 hours or when rain is imminent. Consult the manufacturer for applications over previously treated steel surface.

Health and Safety

*Fibre-Prime* is non-toxic and non-flammable. Your skin might be sensitive to cement. We recommend use of rubber gloves. Avoid contact with skin. If contact occurs, flush immediately with water. Seek medical advice if irritation occurs. Harmful if digested. Keep product out reach of children. FOR INDUSTRIAL USE ONLY. Consult MSDS for additional information.

Color

Dark Grey.

Packaging

*Fibre-Prime* consists of dry Component A supplied in a 11 kg (24.23 lb) bag and liquid Component B, supplied in 2.5 L (0.65 USG) plastic jug.

Yield

One unit of *Fibre-Prime* yields 6.5 L (0.23 ft³) and will cover approximately 3.16 m² (33.0 ft²), or 63lineal m (200 lineal ft) of 15 mm (5/8 in) rebar, applied in two (2) coats around the circumference of the rebar.

Gemite Products Inc.  
March 2005

9 & 3

109870 Coating Systems-Steel Rustproofing  
03700 Concrete Restoration

### Storage and Transportation

When stored on pallets in a dry, cool area the shelf-life of the dry Component A is 12 months. The liquid Component B must not freeze. Packaged 60 kits per pallet.

### TECHNICAL DATA

Compressive Strength	30.0 MPa (4500 psi)
Adhesion to steel	3.5 MPa (500 psi)
Freeze/Thaw Resistance (ASTM C666-A)	0% loss
Resistance to Chloride Penetration (AASHTO T277)	430-520 Coulombs

### INSTALLATION

Current Guide Specification and Application Instructions contain additional information specific to each application and must be followed. Contact Gemite's Technical Service for information specific to your application.

### Surface Preparation

Remove all loose rust, grease, dust and dirt from the rebar surface using sandblasting or steel wire brush.

### Mixing

Place the liquid Component B into a clean container. Add dry Component A while mixing, using a drill (400-600 rpm) with a mixing paddle, until a smooth and lump-free brushable mix is obtained. Allow to sit for 3-5 minutes, then re-mix. Mix only the amount of material which can be applied within 45 minutes after mixing. Discard any material not used within 50 minutes.

### Application

Apply a thin coat of *Fibre-Prime* by brushing onto the steel surface. Let dry for 10-15 minutes and apply the second coat. Apply a minimum of two coats. Repair mortar should be applied in to still "green" *Fibre-Prime*. Shotcrete should be applied within 24 hours.

### Curing

Cure by air drying.

### Clean Up

Tools must be cleaned with water immediately after use. Cured material can only be removed mechanically.

### AVAILABILITY AND COST

*Fibre-Prime* is available worldwide. Contact the manufacturer for the name of the nearest Gemite Representative or Distributor and pricing information.

### MAINTENANCE

None Required.

### WARRANTY

A limited twelve (12) month Material Replacement Warranty is available. For details, contact Gemite's head office.

### TECHNICAL SERVICE

For advice on suitability of *Fibre-Prime* for a specific application, specification assistance and application instructions, contact Technical Service: US 888-443-6483 or Canada 905-672-2020.

### Short Specification

The steel rustproofing and/or coating will be *Fibre-Prime*, manufactured by Gemite Products Inc., [USA 888-443-6483] [Canada 905-672-2020]. It will meet all the following requirements:

Compressive Strength	30.0 MPa (4500 psi)
Adhesion to steel	3.5 MPa (500 psi)
Freeze/Thaw Resistance (ASTM C666-A)	0% loss
Resistance to Chloride Penetration (AASHTO T277)	430-520 Coulombs