

PRODUCT NAME

Gem-Crete® TO ST

(Thin Overlay)
Waterproofing Traffic Topping

MANUFACTURER

Gemite® Products Inc.

Toll Free: 888-4-GEMITE (888-443-6483)

E-mail: techinfo@gemite.com

Web Site: www.gemite.com

USA

160-3480 East Robinson Rd.

Amherst, New York 14228

Phone 888-443-6483

Fax 888•443•6329

CANADA

1787 Drew Road

Mississauga, Ontario L5S 1J5

Phone 905-672-2020

Fax 905•672•6780

FEATURES

- High flow material, almost self-leveling
- Waterproofing
- Stops chlorides
- High strength and abrasion resistance (wet or dry)
- Superior workability & easy application
- High bond to wet concrete
- Breathable
- Highly freeze/thaw resistant
- Nonflammable & nontoxic
- Economical

PRODUCT DESCRIPTION

Basic Use

Surfacing and waterproofing of parking decks, industrial floors, loading docks and patios. Waterproofing and repair of concrete exposed to high concentrations of salt solutions and weak acids.

Composition and Materials

Gem-Crete TO ST is a Portland cement based, polymer and silica fume modified material, especially formulated for protection and waterproofing of concrete. The combination of polymers and inorganic fillers provides excellent resistance to water, salt and weak acids. The chemical composition and aggregate formulation provides high abrasion resistance.

Limitations

Do not apply *Gem-Crete TO ST* when the temperature is expected below 4°C (40°F) within 48 hours or when rain is imminent. Use Hot Weather concreting precautions when applying in temperatures exceeding 25°C (77°F) or under sunny and windy conditions.

Health and Safety

Gem-Crete TO ST is nontoxic and nonflammable. Your skin might be sensitive to cement. We recommend use of rubber gloves. Avoid contact with eyes and prolonged contact with

skin. If contact occurs, flush immediately with water. Seek medical advice if irritation occurs. Harmful if digested. Keep product *out of reach of children*. FOR INDUSTRIAL USE ONLY. Consult MSDS for additional information.

Color

Available in Industrial grey, light grey and off-white colors.

Packaging

Gem-Crete TO ST premix is packaged in 22.7 kg (50 lb) bags.

Yield

Gem-Crete TO ST premix yields approximately 12.2 L (0.43 ft³) and covers approximately 4.1 m² @ 3 mm (41.3 ft² @ 1/8") thickness per bag.

The actual coverage will depend on surface roughness and the thickness applied. The applicator must carry out a sample application to determine the actual coverage for the given substrate and application thickness.

Storage and Transportation

Gem-Crete TO ST when stored on pallets in a dry, cool area, free-from moisture, has a shelf-life of 12 months. Packaged 55 bags (Premix) per pallet.

TECHNICAL DATA (Industrial Grey)

Modulus of Rupture (ASTM C348)	5.5 - 6.9 MPa (800 - 1,000 psi)
Compressive Strength (ASTM C109)	37.9 - 48.3 MPa (5,500 -7,000 psi)
Freeze/Thaw Resistance (ASTM C666, Procedure A)	less than 1% weight loss after 300 cycles
Direct Tension Bond	2.0-2.8 MPa (300 - 400 psi)
Salt Scaling Resistance (ASTM C672)	after 50 freeze/thaw cycles, no scaling
Toxicity	non-toxic in wet or dry form

INSTALLATION

Current Guide Specification and Application Instructions contain additional information specific to each application and must be followed. Gemite's Technical Service must be consulted before starting a project to ensure that the correct surface preparation and application procedures are followed.

Surface Preparation

Remove all loose, delaminated or oil contaminated concrete. Clean the surface by shotblasting, scarifying or a high pressure waterblast with sand to remove laitance, dust and dirt and open capillary porosity.

Gemite Products Inc.
Revised July 2004

3 & 7

03550 Concrete Topping
07570 Traffic Topping

Reinforcing Steel

Clean the reinforcing steel and apply two coats of *Fibre-Prime* as rustproofing layer. Patch deeper holes (over 9 mm, 3/8 in) with *Fibre-Patch OV or ST*.

Crack Treatment

All cracks in the substrate must be treated separately (see Guide Specification).

Mix Design	Metric	US
<i>Gem-Crete TO ST</i> Premix	22.7 kg	50 lb
Water	3.6-3.8 L	0.95-1.0 USG

Mixing

Use a paddle or helix screw type mortar mixer. Place most of the water into the mixer. Gradually add the dry powder and mix thoroughly until completely free of lumps. Adjust the water for suitable workability. Do not over mix. Convey mixed material to the point of placement in clean, uncontaminated containers. The pot life is approximately 45 minutes, depending on the temperature and relative humidity.

Application

Wet the surface with water for a minimum of 6 hours to obtain saturated surface dry (SSD) condition. Apply *Gem-Crete TO ST* in two coats to build approximately 3 - 6 mm (1/8 - 1/4 inch) thick, uniform layer. Brush in the first coat and within 45 minutes apply the second coat by using a squeegee. Provide a broom finish.

Curing

Air dry cure for 2-3 days. Protect against rapid evaporation, or plastic shrinkage cracking may occur. Use surface evaporation retarder, *Adi-Con SER* or “fogging” under the sunny and windy conditions to avoid plastic shrinkage cracking. When working under tarps at freezing temperatures, use electrical heaters. Avoid using propane heaters to prevent “carbonation” of the material.

Clean Up

All tools must be cleaned with water immediately after use. Cured material can only be removed mechanically.

AVAILABILITY AND COST

Gem-Crete TO ST is available worldwide. Contact the manufacturer for the name of the nearest Representative/Distributor and current pricing information.

MAINTENANCE

None required.

WARRANTY

A limited twelve (12) month Material Replacement Warranty is available. For complete details contact Gemite’s Head Office.

TECHNICAL SERVICE

For technical advice on suitability of *Gem-Crete TO ST* for specific application, specification assistance and application advice, contact Gemite Products Inc. Technical Service in the USA at (888) 443-6483, in Canada at (905) 672-2020.

Short Specification

The waterproofing topping (concrete surfacing) will be *Gem-Crete TO ST*, polymer, silica fume modified, waterproofing mortar manufactured by Gemite Products Inc., (888-443-6483 (USA) or 905-672-2020 (Canada).