

PRODUCT NAME

Deck-Prime 200

Concrete Deck Primer

MANUFACTURER

Gemite® Products Inc.

Toll Free: 888-4-GEMITE (888-443-6483)

E-mail: techinfo@gemite.com

Web Site: www.gemite.com

USA

160-3480 East Robinson Rd.

Amherst, New York 14228

Phone 888-443-6483

Fax 888-443-6329

CANADA

1787 Drew Road

Mississauga, Ontario L5S 1J5

Phone 905-672-2020

Fax 905-672-6780

FEATURES

- Excellent adhesion
- Moderate to slow drying
- Easy to apply
- Economical

PRODUCT DESCRIPTION

Basic Use

Deck-Prime 200 is used to precondition all surfaces on which Deck-Seal100 and 200 preformed membranes are to be applied. It can be used when ambient and substrate temperatures are above -4°C (25°F). Deck-Prime 200 is an integral component of the Deck-Seal 100 and 200 waterproofing systems.

Composition and Materials

Deck-Prime 200 is a solvent-based, asphalt primer, specifically formulated to provide good initial adhesion and excellent permanent adhesion of Deck-Seal 100 and 200.

Limitations

Deck-Prime 200 is nontoxic, but your skin might be sensitive to rubberized asphalt. Avoid prolonged and repeated skin contact. Keep product out of reach of children. FOR INDUSTRIAL USE ONLY. Consult MSDS for additional information.

Color

Deck-Prime 200 is black in color.

Packaging

Deck-Prime 200 is supplied in 19 L (5.26 USG) pails or 209 L (55 USG) drums.

Shelf Life, Storage and Transportation

Two years in unopened containers. Store at temperatures above 4°C (39°F) and less than 29°C (85°F). Store and transport as combustible liquid. Use reasonable care in transportation. Protect from inclement weather when storing on site.

Coverage

The coverage is approximately 2.5-4.9 m²/L (100-200 ft²/USG).

TECHNICAL DATA

Property	Value
Weight	0.92 kg/L (7.69 lbs/USG)
Solids Content	65 % by weight
Color	Black
Tack-Free Time	4 hours at 24 °C (75°F)
Flash Point	39°C (102°F)

INSTALLATION

Application

Deck-Prime 200 may be applied by explosion proof sprayer, roller or brush. Vapors during spray applicator may be hazardous. Wear appropriate protection. Use a heavy nap roller with natural material such as wool to avoid deterioration. Spread primer evenly and do not build up thick film. Avoid deep puddles which will lengthen dry time and will build a thick film. Allow Deck-Prime 200 to be tack-free. On warm days drying will occur more rapidly. Priming should be limited to what can be covered with Deck-Seal100 and 200 in one working day. Any areas not covered with Deck-Seal 100 and 200 during the day may require additional priming. Be sure to cover open pails when not in use. Clean tools with mineral spirits or paint thinner at the end of each day. (Mineral spirits and paint thinner are combustible liquids and should be used with care).

AVAILABILITY AND COST

Contact Gemite Products Inc. for the name of the Representative/Distributor nearest you and pricing information.

MAINTENANCE

None required

WARRANTY

A limited twelve (12) month Material Replacement Warranty is available. For complete details contact Gemite's Head Office.

TECHNICAL SERVICE

For technical advice on the suitability of Deck-Prime 200 for a specific application, specification assistance and application advice, contact Gemite Technical Service: USA 888-443-6483 or Canada 905-672-2020.

Short Specification

The primer for Deck-Seal 100 or 200 self-adhesive waterproofing membrane will be Deck-Prime 200 manufactured by Gemite Products Inc. [USA 888-443-6483], [Canada 905-672-2020]. It will be applied according to the current manufacturer's specifications and recommendations. The suitability of the surface preparation method must be checked with Gemite Technical Service before starting each project.

